

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

## **IMAGES ARE BEST AVAILABLE COPY.**

As rescanning documents *will not* correct images,  
Please do not report the images to the  
Image Problem Mailbox.

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> <b>B32B 3/00, 7/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 94/23941</b> <b>(43) International Publication Date:</b> 27 October 1994 (27.10.94)
<b>(21) International Application Number:</b> PCT/US94/04346 <b>(22) International Filing Date:</b> 20 April 1994 (20.04.94) <b>(30) Priority Data:</b> 051,120 21 April 1993 (21.04.93) US <b>(71) Applicant:</b> MOBIL OIL CORPORATION [US/US]; 3225 Gallows Road, Fairfax, VA 22037-0001 (US). <b>(72) Inventors:</b> BALLONI, Riccardo; Via DeGasperi, 7, Vedano, Al Lambro, I-Milano (IT). TSAI, Mingliang, Lawrence; Apartment A, 8 Pamela Lane, Rochester, NY 14618 (US). <b>(74) Agents:</b> SUNG, Tak, K. et al; Mobil Oil Corporation, 3225 Gallows Road, Fairfax, VA 22037-0001 (US).		<b>(81) Designated States:</b> AU, CA, CZ, HU, JP, KR, PL, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> MULTILAYER PACKAGING FILMS  <b>(57) Abstract</b> <p>A biaxially oriented multilayer film structure comprising: (A) a core layer of polypropylene having dispersed therein microspheres sufficient in size and quantity so that, during orientation, the core layer becomes opaque, which either includes a minor proportion of a maleic anhydride modified polypropylene blended therein and/or has a skin layer (B) of maleic anhydride modified polypropylene on one side; (C) a layer of ethylene vinyl alcohol (EVOH) copolymer on the maleic anhydride modified polypropylene containing layer, and (D) on the other side of the core layer a heat sealable or printable skin layer; said structure comprising polypropylene of greater orientation in the transverse direction.</p> <p><i>Refs mentioned in I.P.D</i></p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MD	Republic of Moldova	TJ	Tajikistan
DE	Germany	MG	Madagascar	TT	Trinidad and Tobago
DK	Denmark	ML	Mali	UA	Ukraine
ES	Spain	MN	Mongolia	US	United States of America
FI	Finland			UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

**MULTILAYER PACKAGING FILMS**

This invention relates to a multilayer film structure which can be metallized and laminated to another film.

5 Structures of the present invention are employed mainly as packaging films utilized in the overwrapping of products or in the formation of bags, cartons or pouch-type containers to contain various food or non-food products. It is necessary that the film structures utilized for this purpose be as resistant  
10 to the transmission of moisture, air and deleterious flavors as possible. No single polymeric film material has the characteristics in and of itself to satisfy this requirement.

It is an object of the invention to present a multilayer packaging film structure having the characteristics to minimize  
15 to a large extent the transmission of gases, water vapor, and flavours through such a film.

In accordance with the present invention a multilayer structure comprises:

(A) a core layer of polypropylene having dispersed  
20 therein microspheres sufficient in size and quantity so that, during orientation, the core layer becomes opaque, which either includes a minor proportion of a maleic anhydride modified polypropylene blended therein and/or has a skin layer (B) of maleic anhydride modified polypropylene on one side;

25 (C) a layer of ethylene vinyl alcohol (EVOH) copolymer on the maleic anhydride modified polypropylene containing layer, and

(D) on the other side of the core layer a heat sealable or printable skin layer;  
30 said structure comprising polypropylene of greater orientation in the transverse direction.

In the multilayer film structure described above it is preferred that the EVOH layer carry a metal layer formed, for example, by metallisation. It is further preferred that a  
35 polymeric film be laminated to the metallized layer so as to add additional gauge, stiffness, puncture resistance and barrier properties to the structure.

- 2 -

In forming the multilayer film structure of the present invention, a core layer of polypropylene having dispersed therein microspheres sufficient in size and quantity so that during orientation the core layer becomes opaque. This core  
5 layer can be as described in U.S. 4,377,616. The preferred polypropylene matrix material has the following characteristics: density 0.90 to 0.91 g/cc; m.p. 160°C or higher; melt flows 2 to 4g/10 min at 230°C. The preferred microspheres are those disclosed in the above mentioned patent and particularly  
10 preferred are microspheres of polybutylene terephthalate, and nylon.

The skin layer of maleic anhydride modified polypropylene which is coextruded on one side of the core layer may be prepared by any process, for example, that disclosed in U.S.  
15 3,433,777; and 4,198,327. A commercially available maleated polypropylene or propylene copolymer has the following physical characteristics: density 0.89 to 0.91 (ASTM D1505), Vicat softening point 100 to 150°C (ASTM D1525); Shore hardness 50 to 70 (ASTM D2240); melting point 140 to 160°C (ASTM D2117). It  
20 is essential to use maleated polyolefin in order to tie the core layer with the EVOH when they are incompatible in their natural state.

The ethylene vinyl alcohol copolymer referred to herein can be obtained from any commercial source. For example, extrusion  
25 grade ethylene vinyl alcohol copolymer (EVOH) is available under the name EVAL from Kuraray Co. Ltd. of Japan. EVOH resin is conventionally prepared by saponifying ethylene vinyl acetate copolymer containing an ethylene content of from 20 to 70 mole %, to a saponification degree of 90% or higher. The ethylene  
30 vinyl alcohol copolymer employed herein can have a ethylene content ranging from 20 to 70 mole %.

The heat sealable layer employed herein and applied during coextrusion can be an ethylene propylene (EP) copolymer or an ethylene propylene butene-1 (EPB) terpolymer, which will be  
35 located on the side of the substrate opposite to the EVOH layer. The ratio of ethylene to propylene to butene-1 can be from 0 to 15% ethylene, 70 to 100% propylene and 0 to 15% butene-1, e.g.,

- 3 -

2% ethylene 94% polypropylene and 4% butene-1.

The printable surface can be any polymer such as polyolefin homopolymer; copolymer and terpolymer; polycarbonate; or polyester. The characteristics of the printable surface is one  
5 with a surface free energy of 34 dynes/cm or higher.

As will be shown below in the specific Examples, the utilization of the EVOH in combination with the metallization of the EVOH and the further coating of the metallization layer with an appropriate lamination film will progressively improve  
10 oxygen barrier, water vapor barrier and aroma barrier characteristics over structures not containing these modifications. The Examples will also show that structures within the scope of the present invention can form hermetic seals. Metallization, which occurs directly on the EVOH, is  
15 accomplished by conventional vacuum deposition. While aluminum is illustrated as the preferred metal it is to be understood that other metals such as zinc and gold, capable of being commercially vapor deposited, can also be employed. Also while polypropylene has been shown as the laminate film to the surface  
20 of the metal layer this is merely by way of illustration. It is to be understood that other films such as other polyolefins, i.e., polyethylene; polybutylene; olefin copolymers; polyamides; polycarbonate; and polyacrylonitrile can also be employed. In forming such laminations an effective adhesive is a hot melt  
25 low density polyethylene applied in an amount of about 10 pounds per ream. Other suitable adhesives can also be employed.

#### EXAMPLE 1

A four layer biaxially oriented film, having an approximate final thickness of 1.4 mil was prepared by coextruding a core  
30 matrix of polypropylene (melt flow 3.0), blended with about 8 wt.% of polybutylene terephthalate (PBT) microspheres. This core comprised about 91% of the coextruded thickness. A skin layer of the maleic anhydride modified polypropylene was coextruded on one side of the core comprising about 1.5% of the  
35 total extruded thickness and a lower skin surface of a heat sealable ethylene-propylene-butene-1 terpolymer comprising 3.5% of the total thickness of the extrudate. The four layer of the

- 4 -

coextrudate is a metal receiving layer of polypropylene comprising 4% of the total extrudate thickness, extruded on the surface of the maleic anhydride modified polypropylene.

The coextrudate was quenched at 30-50°C, reheated to 115-  
5 125°C and stretched in the machine direction 5 times using transport rolls operating at different speeds. Thereafter, the film was transversely oriented 8 times at a temperature profile ranging from 155°C-180°C. During this latter orientation the film structure turned opaque. Thereafter, the metal receiving  
10 polypropylene layer was surface treated with corona discharge. Alternatively the surface can be flame treated to the appropriate surface free energy conducive for metal adhesion.

The film was metallized by vacuum deposition of aluminum and tested for metal pick-off by Scotch 610 tape (3M Corp). To  
15 test the metal adhesion, strips of Scotch 610 tape were applied to the metallized surface. The tape was pulled manually. The tape pull test was repeated 3 times with fresh tape applied to the same area.

Table 1, below, shows the film properties prior to  
20 metallization. Table 2 shows the properties after metallization.

The metallized upper layer was subsequently laminated to a layer of polypropylene film approximately 0.75 mil thick. This was adhesively bonded with 10 pounds of per ream of molten  
25 LDPE adhesive at a melt temperature of 325°C in a laminating machine. Table 3 shows the resultant laminate properties.

#### EXAMPLE 2

A four layer biaxially oriented film structure was prepared in the following manner: The same polypropylene core matrix with  
30 PBT as employed in Example 1 was coextruded with the same maleic anhydride modified polypropylene in the same dimensions on one side of said core and on the modified polypropylene layer, a layer of EVOH with 48 mole % ethylene content, was simultaneously coextruded thereon. On the opposite side of the  
35 core the same heat sealable resin as in Example 1 was applied in the same thickness. This four layer coextrudate was quenched at 30-50°C, reheated to 115-125°C and stretched in the machine

- 5 -

direction 5 times using transport rolls operating at different speeds. Thereafter, the film was transversely oriented 8 times at a temperature profile ranging from 155°-180°C. Thereafter, the EVOH layer was corona discharge treated. Subsequently, the EVOH layer was metallized in the manner of Example 1. The metallized structure was then laminated as in Example 1.

#### EXAMPLE 3

A four layer biaxially oriented film structure identical to that of Example 2 except the EVOH layer is 2% rather than 4% of the thickness prior to metallization and the heat seal ethylene-propylene-butene-1 layer is 11.5% of the thickness rather than 3.5% prior to metallization.

#### EXAMPLE 4

A four layer biaxially oriented film prepared as in Example 1, except that the metallizing layer was not corona discharge treated. The film was metallized as in Example 1. The metallized upper layer was subsequently laminated to a three layer unbalanced oriented HDPE film having an approximate final thickness of 1.15 mils. This three layer structure consisted of a primary high density polyethylene core layer wherein the core comprised 83% of the film thickness. On one surface of the core was a heat seal layer of ethylene-propylene-butene-1 terpolymer which comprises 3% of the total thickness of this three layer structure. The other surface of this core layer comprised 14% of the overall film thickness and was also ethylene-propylene-butene-1 terpolymer. This three layer structure was laminated to the metallized surface with 10 pounds per ream of molten LDPE (density 0.90-0.92) at a melt temperature of 325°C employing a commercial poly laminating machine.

#### EXAMPLE 5

A four layer biaxially oriented film having an approximate final thickness of 1.40 mil was prepared by coextruding a polypropylene core matrix blended with about 8 wt.% of polybutylene terephthalate (PBT) microspheres. The core matrix made up 95% of the film thickness. An adhesion promoting layer of a maleic anhydride modified polypropylene (with a melt flow of 3.0) comprising 1.5% of the total thickness. On the opposite

- 6 -

surface of the core was coextruded a printable surface layer of high density polyethylene comprising 1.5% of the total thickness. On the surface of the modified polypropylene there was simultaneously coextruded a surface layer of EVOH copolymer  
5 with 48 mole % ethylene content. After the desired machine direction orientation the film was transversely oriented 8 times at a temperature profile ranging from 155°-180°C which produced a visible white opaque appearance. Thereafter, the printable high density polyethylene layer was corona discharge treated to  
10 a level of 38 dynes per cm. Following this, the same three layer lamination web structure as employed in Example 4 was laminated to the aluminum surface in the same manner as Example 4. Tables 1, 2 and 3 show the results of the characteristics of the several films.

15

- 7 -

TABLE 1

## 5                      Film Properties Prior to Metallization

	<u>EXAMPLE</u>	<u>TREATMENT LEVEL DYNES/CM</u>	<u>WATER VAPOR TRANS*</u>	<u>OXYGEN TRANS**</u>	<u>METAL PICKOFF%</u>	<u>AROMA BARRIER</u>	<u>HERMETIC SEAL</u>
10	1	38	0.40	125	80	NO	NO
	2	>52	0.43	3.3	0	YES	NO
	3	>52	0.43	7	0	YES	YES
	4	29	0.40	125	100	NO	NO
15	5	42	0.43	7	0	YES	NO

\* gH<sub>2</sub>O/100 in.<sup>2</sup>/24 hrs.20 \*\* ccO<sub>2</sub>/100 in.<sup>2</sup>/24 hrs.

25

TABLE 2

## 30                      Film Properties After Metallization

	<u>EXAMPLE</u>	<u>LIGHT TRANSMIS</u>	<u>WATER VAPOR TRANS</u>	<u>OXYGEN TRANS</u>	<u>AROMA BARRIER</u>	<u>HERMETIC SEALS</u>	<u>LAMINATION BONDS**</u>
35	1	<1%	0.15	42	NO	NO	80
	2	<1%	0.01	0.01	YES	NO	200
	3	<1%	0.015	0.015	YES	YES	180
	4	<1%	0.25	100	NO	NO	50
40	5	<1%	0.005	0.01	YES	NO	200

\* gH<sub>2</sub>O/100 in.<sup>2</sup>/24 hrs.45 \*\* ccO<sub>2</sub>/100 in.<sup>2</sup>/24 hrs.

50

- 8 -

TABLE 3

## Film Properties After Lamination

5

10	<u>EXAMPLE</u>	<u>TRANSMIS</u>	<u>WATER</u>	<u>OXYGEN</u>	<u>AROMA</u>	<u>HERMETIC</u>	<u>POUCH</u>
			<u>VAPOR</u>	<u>TRANS*</u>	<u>BARRIER</u>	<u>SEALS</u>	<u>MACHINABIL</u>
	1	<1%	0.10	42	NO	NO	ACCEPTABLE
	2	<1%	0.01	0.01	YES	NO	ACCEPTABLE
	3	<1%	0.015	0.015	YES	YES	ACCEPTABLE
15	4	<1%	0.25	100	NO	YES	EXCELLENT
	5	<1%	0.005	0.01	YES	YES	EXCELLENT

20

\*  $\text{gH}_2\text{O}/100 \text{ in.}^2/24$   
 \*\*  $\text{ccO}_2/100 \text{ in.}^2/24$

- 9 -

In Tables 2 and 3 under the heading "Aroma Barrier" there is an indication as to whether or not the film samples are an effective barrier to aromas. In order to test the effectiveness of the film structures in excluding deleterious odors, flavors and aromas from a product susceptible of absorbing such flavors, etc., several packages were wrapped and sealed with the film. All of the packages were placed in a controlled environment which exposed them to an aromatic hydrocarbon that provided a typical or potential odorant that can be readily identified chemically and measured quantitatively. In this case the aromatic hydrocarbon was toluene. Individual packages were withdrawn from the controlled environment in a timed sequence. A small air sample was then taken from within the package with a hypodermic syringe. The sample was analyzed chromatographically. The chromatographic peak stayed low as time progressed and raised only slowly at longer times. The test was carried out over a time period of from 0-200hrs. This revealed that the subject multilayer structure is an excellent odor, flavor and aroma barrier that can be used to protect flavor sensitive products.

Table 1 shows that Example 1 is a poor structure in so far as the transmission of water vapor and oxygen transmission is concerned. Example 1 also does not provide an excellent surface for the bonding of metal thereto. The structure of Example 1 also could not form a hermetic seal. Example 2 shows that the addition of an EVOH copolymer layer causes a dramatic drop in the amount  $O_2$  transmitted and is an aroma barrier in comparison to Example 1. Example 2 shows that this structure has significant resistance to metal pickoff by the tape test. A hermetic seal could not be formed with the structure. Example 3 shows no decrease in the amount of water vapor transmission and aroma barrier and the greater thickness of the heat seal ethylene-propylene-butene-1 copolymer layer permitted the formation of an hermetic seal. Example 4, which did not employ an EVOH layer, showed that the oxygen transmission had again increased greatly to 125 grams per 100in<sup>2</sup> per 24 hrs. It was not effective as an aroma barrier. In addition, there was no meaningful adhesion of the metal to the metal receiving

- 10 -

untreated propylene layer. Example 5 of Table 1 again demonstrates the effectiveness of EVOH in minimizing oxygen transmission and metal pickoff even without any surface treatment prior to metallization. A hermetic seal could be  
5 formed with this structure. In all cases Table 1 shows that the structures had a Tappi opacity of 71.

Table 2 illustrates the properties of the structures after metallization. By metallizing Example 1 the water vapor transmission was reduced by a significant amount to 0.15 grams  
10 per 100in<sup>2</sup> per 24 hours. The metallization alone caused a significant reduction in the oxygen transmission however the structure was not effective as an aroma barrier. In addition, a hermetic seal could not be formed with the structure. Example 2 showed that the combination of the EVOH copolymer and  
15 metallization produced the water vapor transmission and the oxygen transmission down to 0.01 grams per 100 in<sup>2</sup> per 24 hours and 0-01cc per 100 in<sup>2</sup> per 24 hours respectively. In addition, the structure was effective as an aroma barrier. A hermetic seal still could not be formed with this structure. Example 3  
20 showed that a significant increase in the thickness of the heat seal permitted the formation of an hermetic seal. Example 4 again shows that the elimination of the EVOH layer is not compensated for by a metallization layer in so far as oxygen transmission and aroma barrier is concerned. Example 5  
25 illustrates that the structure with the untreated EVOH layer in combination with the metallization reduces the water vapor transmission to a rate of 0.005 grams per 100 in<sup>2</sup> per 24 hours and reduces the oxygen transmission to a level of 0.01. This structure is an aroma barrier. Examples 2, 3 and 5 also  
30 illustrate that high lamination bonds are formed with these structures.

Table 3 shows the multi-layer structure properties after lamination to a polymeric film structure. Example 1 which shows the structure laminated to oriented polypropylene is a poor  
35 structure as far as oxygen transmission is concerned. In addition the structure is not an effective aroma barrier and does not permit the formation of hermetic seals. In commercial

- 11 -

machinery which forms packaging pouches, the machinability of the structure is merely acceptable. Example 2 shows that the structure with EVOH and oriented polypropylene as the laminate is effective as regards water vapor transmission, oxygen  
5 transmission, aroma barrier but is not acceptable in the formation of a hermetic seal. Example 3 with a decreased thickness of EVOH and an increased thickness of the heat seal is effective from a water vapor and oxygen transmission standpoint. It also is effective as a aroma barrier structure  
10 and it does form hermetic seals. Like examples 1 and 2 it is merely acceptable as far as machinability is concerned. Example 4 again shows that without the EVOH oxygen transmission is significantly higher and the structure is not an effective aroma barrier. Example 5 shows excellent commercial characteristics  
15 in all respect, including, low water vapor transmission and low oxygen transmission. It is an effective aroma barrier and produces hermetic seals and is excellent as far as machinability is concerned.

20

25

30

35

- 12 -

CLAIMS:

1. A biaxially oriented multilayer film structure comprising:
  - (A) a core layer of polypropylene having dispersed therein microspheres sufficient in size and quantity so that, during orientation, the core layer becomes opaque, which either includes a minor proportion of a maleic anhydride modified polypropylene blended therein and/or has a skin layer (B) of maleic anhydride modified polypropylene on one side;
  - (C) a layer of ethylene vinyl alcohol (EVOH) copolymer on the maleic anhydride modified polypropylene containing layer, and
  - (D) on the other side of the core layer a heat sealable or printable skin layer;said structure comprising polypropylene of greater orientation in the transverse direction.
2. A film structure according to claim 1 wherein the machine direction orientation is from 3 to 7 times and the transverse direction orientation is from 7 to 12 times.
3. The structure of any preceding claim wherein the EVOH copolymer layer has been treated to a surface free energy of greater than 33 dynes/cm.
4. The structure of any preceding claim wherein the EVOH copolymer layer has been treated by corona discharge or by flame treatment.
5. The structure of any preceding claim wherein the EVOH copolymer layer carries a metal layer thereon.
6. The structure of claim 5 wherein the metal layer comprises aluminum.
7. The structure of any preceding claim wherein a polymeric film is laminated to the metal layer.

- 13 -

8. The structure of claim 7 wherein the polymeric film comprises oriented or unoriented, transparent or opaque polyolefin.

9. The structure of claim 8 wherein the lamination is effected  
5 by a low density polyethylene adhesive.

10. The structure of any preceding claim wherein the heat sealable skin layer comprises an olefin homopolymer, copolymer or terpolymer.

10

11. The structure of claim 10 wherein the terpolymer comprises an ethylene/propylene/butene-1 terpolymer.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/04346

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(5) : B32B 3/00, 7/00.

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 428/516, 910, 461, 323, 349.

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 5,153,074 (MIGLIORINI) 06 October 1992, Abstract and column 3, lines 8-11.	1-3
Y	US, A, 4,377,616 (ASHCRAFT ET AL) 22 March 1983, column 1, lines 41-66.	1-3
Y	US, A, 4,966,795 (GENSKE ET AL) 30 October 1990, column 1, lines 27-34.	1-3

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be part of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combinations being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means		
*P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

08 JUNE 1994

Date of mailing of the international search report

JUN 29 1994

 Name and mailing address of the ISA/US  
 Commissioner of Patents and Trademarks  
 Box PCT  
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

E. ROLLINS BUFFALOW

Telephone No. (703) 308-2351

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/04346

## A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

428/516, 910, 461, 323, 911, 913, 407, 318.4, 35.7, 35.8, 36.6, 34.7, 349.

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US94/04346

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:  
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☒ Claims Nos.: 4-11  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.  
☐ No protest accompanied the payment of additional search fees.